

Technical Data Sheet

Fibracon[®] PTFE + 25% Glass

Typical characteristics

- FDA approved grades of glass filled PTFE are available
- Improved wear properties
- Reduced deformation under load

Typical industries

- 화학 가공 산업
- 차량 제조
- 전자 제품
- Oil and Gas
- 기계 공학 산업
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Density	ASTM D4894	g / cm ³	2.24
Mechanical properties			
Hardness	Needle	Shore D	64
Tensile Strength (23°C)	ASTM D4894	MPa	18
Elongation at Break	ASTM D4894	%	200
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

