Röchling

Technical Data Sheet

Fibracon[®] PTFE + 33% Carbon + 2% Graphite

PTFE

load

Typical characteristics Improved thermal and

electrical conductivity

Good wear resistance

• Reduced deformation under

Typical industries

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering Industry
 - Healthcare
- Food IndustryWind Energy

	Test method	Unit	Guideline value
General properties			
Density	ASTM D4894	g / cm ³	2.04
Mechanical properties			
Hardness	Needle	Shore D	64 - 70
Tensile Strength (23°C)	ASTM D4894	MPa	12
Elongation at Break	ASTM D4894	%	40
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



Print: 30/04/2025 • Release: 20/09/2023 PIM-Version: 37 • PIM-ID: 709619 • PIM-Code: 37-40-13.14.143-7.7.8.5.5.9.5.10-1 Company-IDs: 21220