

### Technical Data Sheet

## Fibracon<sup>®</sup> PTFE + Anti-Static Filler

PTFE

#### Typical characteristics

- La adición de carbono confiere propiedades antiestáticas al material.
- Hay grados disponibles donde la materia prima ha sido aprobada según los estándares de la FDA.

#### Typical industries

- Construcción de contenedores químico
- Construcción de vehículos
- Electrónica
- Petróleo y gas
- Construcción de máquinas e instalaciones
- Healthcare
- Industria alimentaria
- Energía eólica

|                              | Test method | Unit                | Guideline value |
|------------------------------|-------------|---------------------|-----------------|
| <b>General properties</b>    |             |                     |                 |
| Density                      | ASTM D4894  | g / cm <sup>3</sup> | 2.15            |
| <b>Mechanical properties</b> |             |                     |                 |
| Hardness                     | Needle      | Shore D             | 56              |
| Tensile Strength (23°C)      | ASTM D4894  | MPa                 | >20             |
| Elongation at Break          | ASTM D4894  | %                   | 250             |
| <b>Thermal properties</b>    |             |                     |                 |
| Service Temperature          |             | °C                  | -200 to +260    |

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 12/12/2025 • Release: 20/09/2023  
 PIM-Version: 33 • PIM-ID: 709628 • PIM-Code: 33-40-14.9-7.7.8.5.5.27.5.10-1  
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

