

Technical Data Sheet

Fibracon[®] PTFE CLF

Typical characteristics

- Low wear
- Non abrasive
- Low coefficient of friction

Typical industries

- 화학 가공 산업
- 차량 제조
- 전자 제품
- Oil and Gas
- 기계 공학 산업
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Specific Gravity	ASTM D4894	-	2.09
Mechanical properties			
Hardness	Needle	Shore D	62
Tensile Strength (Cross Direction)	ASTM D4894	MPa	28
Elongation	ASTM D4894	%	320
Deformation under load	13.7MPa, 23°C 24h	%	8.2
Wear factor	Thrust type / ring on ring P=0.45 MPa, V=1.0 m/s Counter material: Al	10 ⁻⁷ mm ³ / (Nm)	18
Coefficient of friction	Thrust type / ring on ring P=0.45 MPa, V=1.0 m/s Counter material: Al	-	0.15
Thermal properties			
Service Temperature		°C	-200 to +260

Typical values - not suitable for specification purposes.

Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 10/05/2024 • Release: 20/09/2023

PIM-Version: 36 • PIM-ID: 709629 • PIM-Code: 36-40-16.7.11-7.6.8.5.5.9.5.10-2

Page 1 / 1 (Dates in DD/MM/YYYY)

