

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE Detectaflon

### Typical characteristics

- X-ray and metal detectable
- Easy to clean, withstands chemical cleaning products and other cleaning processes

### Typical industries

- Výroba nádrží a zařízení pro chemický průmysl
- Výroba vozidel
- Elektronika
- Ropa a plyn
- Stavba strojů a zařízení
- Healthcare
- Potravinářský průmysl
- Větrná energie

	Test method	Unit	Guideline value
<b>General properties</b>			
Specific Gravity	ASTM D4894	-	2.32
<b>Mechanical properties</b>			
Hardness	Needle	Shore D	63
Tensile Strength (23°C)	ASTM D4894	MPa	28
Elongation at Break	ASTM D4894	%	300
Coefficient of friction (Dynamic)	ISO 7148 *	-	0.22
Wear rate	ISO 7148 *	mm/h	0.022
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material, and should only be used as a guide to the generic material performance.

\*ISO 7148 - Tribo starting conditions Pin on ring ISO 7148 Load= 3.5 N Rotating Speed= 4 m/sec Temp.= 80°C Counter-surface= STST Ra= 0.25-0.35 μm Contact area of the pin: 78.5 mm<sup>2</sup>

