

Technical Data Sheet

Fibracon[®] PTFE Detectaflon

Typical characteristics

- X-ray and metal detectable
- Easy to clean, withstands chemical cleaning products and other cleaning processes

Typical industries

- Химическая промышленность
- Строительство транспортных средств
- Электронная промышленность
- Нефтегазовая отрасль
- Машиностроение
- Healthcare
- Пищевая промышленность
- Ветроэнергетика

	Test method	Unit	Guideline value
General properties			
Specific Gravity	ASTM D4894	-	2.32
Mechanical properties			
Hardness	Needle	Shore D	63
Tensile Strength (23°C)	ASTM D4894	MPa	28
Elongation at Break	ASTM D4894	%	300
Coefficient of friction (Dynamic)	ISO 7148 *	-	0.22
Wear rate	ISO 7148 *	mm/h	0.022
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material, and should only be used as a guide to the generic material performance.

*ISO 7148 - Tribo starting conditions Pin on ring ISO 7148 Load= 3.5 N Rotating Speed= 4 m/sec Temp.= 80°C Counter-surface= STST Ra= 0.25-0.35 µm Contact area of the pin: 78.5 mm²

Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 03/05/2024 • Release: 20/09/2023

PIM-Version: 33 • PIM-ID: 709598 • PIM-Code: 33-40-6.13-7.6.8.5.5.9.5.10-4

Page 1 / 1 (Dates in DD/MM/YYYY)

