

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE FGB

### Typical characteristics

- Low coefficient of friction
- Non-stick

### Typical industries

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering Industry
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
<b>General properties</b>			
Specific Gravity	ASTM D4894	-	2.17
<b>Mechanical properties</b>			
Hardness	Needle	Shore D	57
Tensile Strength (Cross Direction)	ASTM D4894	MPa	32
Elongation (Cross Direction)	ASTM D4894	%	330
<b>Thermal properties</b>			
Service Temperature		°C	-200 +260
<b>Compliance properties</b>			
Compliant to food contact guidelines	FDA 21 cfr 177.1550		raw material only

This declaration refers to raw material and does not necessarily cover the finished product. The raw material used complies with the following regulations and standards: - FDA Directive 21 CFR 177.1550 (Fluoropolymers) PTFE may be safely used as additive in articles intended to come in contact with foodstuff. - FDA Directive 21 CFR 178.3297 (Colorants for Polymers). The product is manufactured exclusively from the raw material and no other substances have been intentionally added. It is the responsibility of the customer to determine whether the finished product and its intended use comply with the laws and regulations.

### Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800  
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 01/05/2024 • Release: 20/09/2023

PIM-Version: 23 • PIM-ID: 709930 • PIM-Code: 23-40-11.8-7.6.8.5.5.9.5.10-2

Page 1 / 1 (Dates in DD/MM/YYYY)

