

### Technical Data Sheet

## Laminex<sup>®</sup> 2010

#### Typical characteristics

- Alta rigidez
- Buenas propiedades eléctricas
- Buena resistencia al aceite y al combustible.

#### Typical industries

- Construcción de máquinas e instalaciones

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,35-1,40
<b>Mechanical properties</b>			
Bending strength	DIN EN ISO 178	MPa	100-140
Tensile modulus of elasticity	DIN EN ISO 527	MPa	5000-7100
Tensile modulus of bending	DIN EN ISO 178	MPa	6500-8200
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	6,5-16
Elongation at break	DIN EN ISO 527	%	1,3-3,0

#### Röchling Industrial Xanten GmbH

Hagdornstraße 3 • 46509 Xanten/Germany (DE) • Tel. +49 2801 76-0  
 info-xan@roechling.com • www.roechling.com/industrial/xanten

Print: 28/04/2024 • Release: 20/09/2023 • Version: 1.0  
 PIM-Version: 40 • PIM-ID: 715328 • PIM-Code: 40-24-7.7.6-5

