

## Technical Data Sheet

# Laminex<sup>®</sup> 2100

### Typical characteristics

- Electrically insulating

### Typical industries

- Mechanical Engineering Industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	~1,40
<b>Mechanical properties</b>			
Bending strength	DIN EN ISO 178	MPa	80-150
Tensile modulus of elasticity	DIN EN ISO 527	MPa	5300-7200
Tensile modulus of bending	DIN EN ISO 178	MPa	5000-8200
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	10-14
Elongation at break	DIN EN ISO 527	%	1,3-3,5

#### Röchling Industrial Xanten GmbH

Hagdornstraße 3 • 46509 Xanten/Germany (DE) • Tel. +49 2801 76-0  
 info-xan@roechling.com • www.roechling.com/industrial/xanten

Print: 29/04/2024 • Release: 20/09/2023 • Version: 1.0  
 PIM-Version: 37 • PIM-ID: 715329 • PIM-Code: 37-24-7-5

