

### Technical Data Sheet

## Laminex<sup>®</sup> 2140

#### Typical industries

- Ingegneria meccanica e impiantistica

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	~1,40
<b>Mechanical properties</b>			
Bending strength	DIN EN ISO 178	MPa	130-150
Tensile modulus of bending	DIN EN ISO 178	MPa	6800-8000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	> 20

#### Röchling Industrial Xanten GmbH

Hagdornstraße 3 • 46509 Xanten/Germany (DE) • Tel. +49 2801 76-0  
 info-xan@roechling.com • www.roechling.com/industrial/xanten

Print: 03/05/2024 • Release: 20/09/2023 • Version: 1.0  
 PIM-Version: 38 • PIM-ID: 715331 • PIM-Code: 38-24-5

