

Technical Data Sheet

LubX[®] AST white

Typical characteristics

- Antistatic
- Good sliding properties
- Excellent dry-running properties
- Good wear resistance

Typical industries

- Mechanical Engineering Industry
- Conveyor Technology & Automation
- Food Industry
- Bakery and Confectionery
- Beverage Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	15
Elongation at yield stress	DIN EN ISO 527	%	23
Tensile modulus of elasticity	DIN EN ISO 527	MPa	510
Impact strength	DIN EN ISO 179	kJ / m ²	50
Shore hardness	DIN EN ISO 868	scale D	60
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 – 135
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	≤10 ⁹

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 28/04/2024 • Draft: 28/04/2024

PIM-Version: 372 • PIM-ID: 718574 • PIM-Code: 372-8-15.222.12.142-5.11.5.4.5-5

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Surface resistivity	DIN EN 62631-3-2	Ohm	$\leq 10^9$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 28/04/2024 • Draft: 28/04/2024

PIM-Version: 372 • PIM-ID: 718574 • PIM-Code: 372-8-15.222.12.142-5.11.5.4.5-5

Page 2 / 2 (Dates in DD/MM/YYYY)

