

Technical Data Sheet

LubX[®] S grey pressed

Typical characteristics

- Energy-saving
- Especially aligned to the sliding partner PET
- Food compliant according to 10/2011/EU
- Good wear resistance

Typical industries

- Ingegneria meccanica e impiantistica
- Tecnologia di trasporto e automazione

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,93
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at yield stress	DIN EN ISO 527	%	>50
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	500
Notched impact strength	DIN EN ISO 179	kJ / m ²	no break
Shore hardness	DIN EN ISO 868	scale A	60
Shore hardness	DIN EN ISO 868	scale D	60
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 ... 135
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230 (*)
Service temperature, long term	Average	°C	-150 ... 230 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 01/05/2024 • Release: 20/09/2023 • Version: 2.0
 PIM-Version: 490 • PIM-ID: 591155 • PIM-Code: 490-26-10.11.9.142-5.11-5



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	$\geq 10^{15}$
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	$> 10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ohm	$\geq 10^{14}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 01/05/2024 • Release: 20/09/2023 • Version: 2.0
 PIM-Version: 490 • PIM-ID: 591155 • PIM-Code: 490-26-10.11.9.142-5.11-5

