

### Technical Data Sheet

## Maywotron<sup>®</sup> PS L

#### Typical characteristics

- Protection of electronic devices from electrostatic phenomena
- Conductive & dissipative

#### Typical industries

- Vacuum Forming
- Electronics
- Semiconductor Dicing

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,1
Water absorption	DIN EN ISO 62	%	< 0,1
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	20
Elongation at break	DIN EN ISO 527	%	47
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1739
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	10
Shore hardness	DIN EN ISO 868	scale D	75
<b>Thermal properties</b>			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,17
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	90
Service temperature, long term	Average	°C	80
Service temperature, short term (max.)	Average	°C	95
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	97
<b>Electrical properties</b>			
Surface resistivity	DIN EN 61340	Ohm	10 <sup>5</sup> - 10 <sup>7</sup>
Volume resistivity	DIN EN 61340	Ohm	10 <sup>5</sup> - 10 <sup>7</sup>

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

#### Röchling Industrial Allgäu GmbH

Hinter den Gärten 20 • 87730 Bad Grönenbach/Germany (DE) • Tel. +49 8334 9857-0  
 info@roechling-maywo.de • www.roechling.com/industrial/groenenbach

Print: 08/05/2024 • Release: 15/03/2024 • Version: 4.0  
 PIM-Version: 70 • PIM-ID: 709708 • PIM-Code: 70-15-11.9-4.8.7-12

