

Technical Data Sheet

Play-Tec® UV-stabilized green

PE-HD / PE 300

Typical characteristics

- Physiologically safe
- UV-stabilized
- Colourfast
- Good machinability
- UV-resistant

Typical industries

- Sport e tempo libero
- Costruzione di navi e imbarcazioni
- Parco giochi
- Imbarcazioni da lavoro e da diporto

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,96
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Flammability (Thickness 3 - 10 mm)	DIN 4102		B2
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>23
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1100
Notched impact strength	DIN EN ISO 179	kJ / m ²	>10
Shore hardness	DIN EN ISO 868	scale D	>60
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-30 ... 80
Service temperature, short term (max.)	Average	°C	100
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	67
Electrical properties			
Dielectric constant	IEC 60250		2,4

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 15/12/2025 • Release: 11/12/2024 • Version: 1.0
PIM-Version: 1004 • PIM-ID: 590987 • PIM-Code: 1004-63-11.9.3.70.15-3.5.8.11-5
Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,0004
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹⁴
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 15/12/2025 • Release: 11/12/2024 • Version: 1.0
PIM-Version: 1004 • PIM-ID: 590987 • PIM-Code: 1004-63-11.9.3.70.15-3.5.8.11-5
Company-IDs: 20000-1

