

Technical Data Sheet

Polystone[®] G B 100 RC + UV-stabilized white

PE-HD (PE 100)

Typical characteristics

- Good stress cracking resistance
- Chemical resistant
- UV-stabilized

Typical industries

- 화학 가공 산업
- 화학물질 저장 탱크

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,95
Water absorption	DIN EN ISO 62	%	0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
MRS classification	ISO TR 9080		PE 100
Approval			DIBt
Melt Flow Rate (MFR 190/5)	DIN EN ISO 1133	g / 10 min	0,22
Moulding Compound PE	ISO 17855		PE,,EACH,57-T003
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1000
Notched impact strength	DIN EN ISO 179	kJ / m ²	>16
Shore hardness	DIN EN ISO 868	scale D	63
FNCT (4.0 MPa, 2 % Arkopal N 100, 80 °C)	ISO 16770	h	>8760
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-50 ... 80
Service temperature, short term (max.)	Average	°C	100

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/DE • Tel. +49 5934 701-0

info@roechling-plastics.com • www.roechling.com/industrial/haren

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 11/04/2026 • Release: 07/04/2026 • Version: 1.0

PIM-Version: 55 • PIM-ID: 776010 • PIM-Code: 55-34-22.33.9-7.7-5

Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	67
Electrical properties			
Dielectric constant	IEC 60250		2,5
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,0004
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹⁴
Comparative tracking index	IEC 60112		600
Arc resistance	IEC 60093	degree	L4 (*)
Dielectric strength	IEC 60243	kV / mm	30

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial SE & Co. KG
 Röchlingstr. 1 • 49733 Haren (Ems)/DE • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 11/04/2026 • Release: 07/04/2026 • Version: 1.0
 PIM-Version: 55 • PIM-ID: 776010 • PIM-Code: 55-34-22.33.9-7.7-5
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

