

Technical Data Sheet

Polystone® M AST - ASTM

PE-UHMW / PE 1000

Typical characteristics

- Good wear properties
- Low coefficient of friction
- Reduces build-up of static & electrical charges

Typical industries

- Agriculture Industry
- Bulk Material Handling
- Conveyor Technology & Automation

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0.94
Water Absorption	ASTM D570	%	<0.01
Mechanical properties			
Wear resistance	Sand-slurry		100
Hardness	ASTM D2240	Shore D	62 - 66
Tensile Strength at yield 73°F	ASTM D638	psi	3000
Tensile Modulus	ASTM D638	psi	100000
Elongation at Break	ASTM D638	%	>290
Flexural Strength	ASTM D790	psi	3200
Compressive Strength	ASTM D695	psi	2900
Coefficient of Friction, Dynamic			0.10-0.22
Coefficient of Friction, Static			0.15-0.20
Thermal properties			
CTE, linear	ASTM D696	in/in/°F	1.1x10 ⁻⁴
Melting Point		°F	266 - 275
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	108
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	2.3
Surface resistivity	ASTM D257	Ω/sq	10 ⁶ - 10 ¹¹
Compliance properties			

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 28/01/2026 • Release: 21/01/2026 • Version: 2.0
 PIM-Version: 49 • PIM-ID: 717957 • PIM-Code: 49-19-126.12.12-6.6.11
 Company-IDs: 23070

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
FDA			No
NSF			No
USDA			No



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 28/01/2026 • Release: 21/01/2026 • Version: 2.0
PIM-Version: 49 • PIM-ID: 717957 • PIM-Code: 49-19-126.12.12-6.6.11
Company-IDs: 23070

