

Technical Data Sheet



Polystone[®] M PIR natural

Typical characteristics

- Low coefficient of friction
- Very good abrasion and wear resistance
- Good impact strength
- Good mechanical properties

Typical industries

- Конвейерные технологии и автоматизация
- Машиностроение

Sustainability

- Post-Industrial-Recycling material

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,93
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>17
Elongation at yield stress	DIN EN ISO 527	%	>18
Elongation at break	DIN EN ISO 527	%	>235
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>550
Notched impact strength	DIN EN ISO 11542	kJ / m ²	>100
Shore hardness	DIN EN ISO 868	scale D	>60
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-250 ... 80
Service temperature, short term (max.)	Average	°C	130
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	>10 ¹⁴
Surface resistivity	DIN EN 62631-3-2	Ohm	>10 ¹⁴

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 04/05/2024 • Release: 17/01/2024 • Version: 3.0
 PIM-Version: 230 • PIM-ID: 751898 • PIM-Code: 230-46-11.121.161.16-11.5-4-5



The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 04/05/2024 • Release: 17/01/2024 • Version: 3.0

PIM-Version: 230 • PIM-ID: 751898 • PIM-Code: 230-46-11.121.161.16-11.5-4-5

Page 2 / 2 (Dates in DD/MM/YYYY)

