

Technical Data Sheet

Polystone® M green extruded

PE-UHMW / PE 1000

Typical characteristics

- Bajo coeficiente de fricción
- Muy buena resistencia a la abrasión y al desgaste.
- Buena resistencia al impacto

Typical industries

- Construcción de máquinas e instalaciones
- Transformadores
- Sistemas de transporte y automatización
- Industria alimentaria
- Procesamiento de carne, pescado y aves de corral
- Productos de bollería y dulces

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,93
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Molecular weight	-	10 ⁶ g/mol	~ 9
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>650
Notched impact strength	DIN EN ISO 11542	kJ / m ²	>100
Shore hardness	DIN EN ISO 868	scale D	>63
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-250 ... 80
Service temperature, short term (max.)	Average	°C	130
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	80

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/12/2025 • Release: 18/08/2025 • Version: 3.0
 PIM-Version: 1008 • PIM-ID: 591013 • PIM-Code: 1008-35-12.126.162-5.5.11.5.5-5
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Electrical properties			
Dielectric constant	IEC 60250		2,3
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,0001
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹⁴
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

