Technical Data Sheet

Polystone® P (Homopolymer) SSAG natural extruded

PP-H

Typical characteristics

- High temperature resistance
- Oxidation inhibitory
- Low moisture absorption
- Approvals under foodstuffs law

Typical industries

- Healthcare
- Food Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	>0,90
Water absorption	DIN EN ISO 62	%	<0,1
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>30
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1500
Notched impact strength	DIN EN ISO 179	kJ / m^2	>4
Shore hardness	DIN EN ISO 868	scale D	>70
Thermal properties			
Melting temperature	ISO 11357-3	°C	162 ... 167
Thermal conductivity	DIN 52612-1	W / (m * K)	0,20
Thermal capacity	DIN 52612	kJ / (kg * K)	1,70
Coefficient of linear thermal expansion	DIN 53752	10^{-6} / K	120 ... 190
Service temperature, long term	Average	°C	0 ... 135
Service temperature, short term (max.)	Average	°C	150
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	90
Electrical properties			
Dielectric constant	IEC 60250		2,4
Dielectric dissipation factor (10^6 Hz)	IEC 60250		0,00019

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/03/2026 • Release: 06/02/2025 • Version: 3.0
PIM-Version: 1138 • PIM-ID: 710125 • PIM-Code: 1138-18-11.9.12.14-27.5-5
Company-IDs: 20000-1

	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	Ω * cm	$>10^{14}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{14}$
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.