

Technical Data Sheet

Polystone[®] P EL black

Typical characteristics

- Electrically conductive

Typical industries

- 화학 가공 산업
- 배기 정화 플랜트
- 환기 플랜트
- 전기 산업

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	20
Elongation at break	DIN EN ISO 527	%	74
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1400
Notched impact strength	DIN EN ISO 179	kJ / m ²	15
Thermal properties			
Melting temperature	ISO 11357-3	°C	165
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	10 ³
Surface resistivity	DIN EN 62631-3-2	Ohm	10 ³

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 10/05/2024 • Draft: 10/05/2024

PIM-Version: 416 • PIM-ID: 591334 • PIM-Code: 416-6-12-7.3.3.11-5

Page 1 / 1 (Dates in DD/MM/YYYY)

