

### Technical Data Sheet

## Polystone<sup>®</sup> P MG - ASTM

#### Typical industries

- Healthcare
- Nauki przyrodnicze
- Przemysł farmaceutyczny

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	0.91
Water Absorption	ASTM D570	%	<0.1
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	72
Tensile Strength at yield 73°F	ASTM D638	psi	4900
Elongation at Break	ASTM D638	%	>400
Flexural Strength	ASTM D790	psi	200000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.0
Coefficient of Friction, Dynamic			0.25-0.28
<b>Thermal properties</b>			
CTE, linear	ASTM D696	in/in/°F	6x10 <sup>-5</sup>
Melting Point		°F	323
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	210
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Surface resistivity	ASTM D257	Ohm/cm	>10 <sup>14</sup>
<b>Compliance properties</b>			
FDA			Yes
USP Class VI	ASTM Certified		Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

#### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
[rep@roechling-plastics.us](mailto:rep@roechling-plastics.us) • [www.roechling.com/industrial/rep-us](http://www.roechling.com/industrial/rep-us)

Print: 09/05/2024 • Release: 26/01/2024 • Version: 2.0  
 PIM-Version: 42 • PIM-ID: 717953 • PIM-Code: 42-21-9.9.8-2

