

Technical Data Sheet

Polystone[®] P copolymer EHS grey - ASTM

Typical characteristics

- High rigidity
- Very good weldability
- Corrosion resistance

Typical industries

- Aquaculture
- Technique des salles blanches
- Traitement de l'eau potable et des eaux usées
- Construction de réservoirs et d'installations chimiques
- Réservoirs de stockage
- Stations de galvanisation
- Centres de décapage d'acier
- Systèmes de ventilation
- Stations de purification d'air

	Test method	Unit	Guideline value
General properties			
Densité	ASTM D792	g / cm ³	0.91
Water Absorption	ASTM D570	%	<0.10
Carbon Black Content	ISO6964	%	n/a
Mechanical properties			
Tensile Strength at Yield	ASTM D638	psi	3500
Hardness	ASTM D2240	Shore D	69
Tensile Elongation	ASTM D638	%	>300
Flexural Modulus	ASTM D790	psi	155000
Compressive Strength	ASTM D695	psi	4000
Izod Impact, Notched	ASTM D256	ft-lb/in	8
Coefficient of Friction, Dynamic			0.25-0.28
Thermal properties			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	6
Melting Point		°F	323
Maximum Service Temperature, Air		°F	230
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	210

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 rep@roechling-plastics.us • www.roechling.com/industrial/rep-us

Print: 09/05/2024 • Release: 20/09/2023

PIM-Version: 34 • PIM-ID: 717984 • PIM-Code: 34-21-10.11.15-5.7.6.7.6.3.5.3.3-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	217
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	2.5
Dielectric strength	ASTM D149		45
Surface resistivity	ASTM D257	Ohm/cm	>10 ¹⁴
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes
ASTM Approval			D-4101

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 rep@roechling-plastics.us • www.roechling.com/industrial/rep-us

Print: 09/05/2024 • Release: 20/09/2023

PIM-Version: 34 • PIM-ID: 717984 • PIM-Code: 34-21-10.11.15-5.7.6.7.6.3.5.3.3-2

