

## Technical Data Sheet

# Polystone® P flex

### Typical characteristics

- Resistencia química
- Duro y resistente a la abrasión
- Soldable con Polystone® P
- Alta elasticidad

### Typical industries

- Construcción de contenedores químico
- Plantas de galvanizado
- Sistemas de ventilación
- Tanques de almacenamiento

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,88
Water absorption	DIN EN ISO 62	%	<0,05
Melt Flow Rate (MFR 190/5)	DIN EN ISO 1133	g / 10 min	0,6
<b>Mechanical properties</b>			
Elongation at break	DIN EN ISO 527	%	>800
Tensile modulus of elasticity	DIN EN ISO 527	MPa	200
Shore hardness	DIN EN ISO 868	scale D	35
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	144

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 03/05/2024 • Release: 16/11/2023 • Version: 3.0

PIM-Version: 561 • PIM-ID: 591189 • PIM-Code: 561-6-27.9.10-7.3.3.6-5

