

Technical Data Sheet

Polystone® PPs CubX® (Homopolymer) grey

PP-H

Typical characteristics

- Flame retardant
- High longitudinal and transversal stiffness
- Good handling
- Low weight
- Good thermal insulation
- Chemical resistant

Typical industries

- Costruzione di serbatoi e impianti chimici
- Impianti galvanici
- Plastics for chemical storage tanks
- Impianti di decapaggio dell'acciaio

	Test method	Unit	Guideline value
Properties for the full cross-ribbed twin-wall sheet			
Thermal conductivity	ISO 8302 Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,14
Density	DIN EN ISO 1183	g / cm ³	0,315
Area weight		kg/m ²	17,67
Weld strength lattice / covering sheets		MPa	≥ 20
Flatness	DIN EN ISO 15860	mm/m	≤ 3
Properties for the covering sheets			
Density, RT	DIN EN ISO 1183	g / cm ³	0,94
Notched impact strength, RT	DIN EN ISO 179 EA1	kJ / m ²	4
Melt flow rate (MFR) 2,16 kg, 230 °C	DIN EN ISO 1133	g / 10 min	0,45
Yield strain, RT	DIN EN ISO 527	%	7,19
Yield stress, RT	DIN EN ISO 527	N/mm ²	32
Thermal properties, along, 150 °C	DIN EN ISO 15013	%	0,33
Thermal properties, transverse, 150 °C	DIN EN ISO 15013	%	0,17
Tensile modulus of elasticity, RT	DIN EN ISO 527	MPa	1300

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 05/12/2025 • Release: 05/05/2025 • Version: 2.0
PIM-Version: 1025 • PIM-ID: 591217 • PIM-Code: 1025-46-14.11.20.14.11.33-7.4.7.6-9
Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



(*) tested on the covering sheets

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 05/12/2025 • Release: 05/05/2025 • Version: 2.0
PIM-Version: 1025 • PIM-ID: 591217 • PIM-Code: 1025-46-14.11.20.14.11.33-7.4.7.6-9
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

