

### Technical Data Sheet

## Polystone<sup>®</sup> PPs EL black extruded

#### Typical characteristics

- Flame retardant
- Antistatique
- Electrically conductive

#### Typical industries

- Construction de réservoirs et d'installations chimiques
- Industrie électronique
- Stations de purification d'air
- Systèmes de ventilation

|   | Test method             | Unit                 | Guideline value  |
|---|-------------------------|----------------------|------------------|
| <b>General properties</b>               |                         |                      |                  |
| Densité                                 | DIN EN ISO 1183-1       | g / cm <sup>3</sup>  | >1,17            |
| Water absorption                        | DIN EN ISO 62           | %                    | <0,1             |
| Flammability (Thickness 3 mm / 6 mm)    | UL 94                   |                      | V0               |
| <b>Mechanical properties</b>            |                         |                      |                  |
| Yield stress                            | DIN EN ISO 527          | MPa                  | >20              |
| Tensile modulus of elasticity           | DIN EN ISO 527          | MPa                  | >1300            |
| Notched impact strength                 | DIN EN ISO 179          | kJ / m <sup>2</sup>  | >4               |
| Shore hardness                          | DIN EN ISO 868          | scale D              | >65              |
| <b>Thermal properties</b>               |                         |                      |                  |
| Melting temperature                     | ISO 11357-3             | °C                   | >145             |
| Thermal conductivity                    | DIN 52612-1             | W / (m * K)          | 0,22             |
| Thermal capacity                        | DIN 52612               | kJ / (kg * K)        | 1,70             |
| Coefficient of linear thermal expansion | DIN 53752               | 10 <sup>-6</sup> / K | 120 ... 190      |
| Service temperature, long term          | Average                 | °C                   | 0 ... 100        |
| Service temperature, short term (max.)  | Average                 | °C                   | 130              |
| Vicat softening temperature             | DIN EN ISO 306, Vicat B | °C                   | 81               |
| <b>Electrical properties</b>            |                         |                      |                  |
| Volume resistivity                      | DIN EN 62631-3-1        | Ohm * cm             | <10 <sup>5</sup> |
| Surface resistivity                     | DIN EN 62631-3-2        | Ohm                  | <10 <sup>5</sup> |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



**Röchling Industrial SE & Co. KG**

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 28/04/2024 • Release: 23/01/2024 • Version: 2.0

PIM-Version: 408 • PIM-ID: 590984 • PIM-Code: 408-37-10.15.12-7.8.3.3-5

Page 2 / 2 (Dates in DD/MM/YYYY)

