

## Technical Data Sheet

# Robaglas®

### Typical characteristics

- UV-resistant
- Excellent sliding and wear behaviour
- low specific weight
- Chemical resistance
- High impact strength and stiffness

### Typical industries

- Paper Industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,97
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB / HB
Molecular weight		g/mol	9,2 * 10 <sup>6</sup>
Color			black
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	200
Tensile modulus of elasticity	DIN EN ISO 527	MPa	670
Notched impact strength	DIN EN ISO 179/1eA	kJ / m <sup>2</sup>	>80
Shore hardness	DIN EN ISO 868 / 15 sec	scale D	64
<b>Thermal properties</b>			
Melting temperature	DIN EN ISO 3146	°C	135
Thermal conductivity	DIN EN ISO 8302	W / (m * K)	0,41
Thermal capacity	DIN 51005	kJ / (kg * K)	1,84
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	200
Service temperature, long term	Average	°C	-200 ... 80
Service temperature, short term (max.)	Average	°C	110



	Test method	Unit	Guideline value
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	10 <sup>10</sup>
Surface resistivity	DIN EN 62631-3-2	Ohm	10 <sup>10</sup>
Comparative tracking index	IEC 60112		600

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

Chemical properties: chemically resistant to all aggressive media with the exception of highly oxidising acids. High resistant to corrosion. This material is resistant to all standard chemicals used in paper production, felt/wire cleaning and corrosion inhibition.

