

Technical Data Sheet

Sustarin[®] H (Delrin[®]) AF - ASTM

POM-H

Typical characteristics

- Good dimensional stability
- Good wear properties
- Good sliding properties

Typical industries

- Conveyor Technology & Automation
- Mechanical Engineering Industry
- Electronics

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	1.50
Water Absorption	ASTM D570	%	0.8
Water Absorption 24 hours	ASTM D570	%	0.2
Dissipation Factor	ASTM D150	1MHz	0.009
Mechanical properties			
Hardness	ASTM D2240	Shore D	85
Tensile Strength at yield 73°F	ASTM D638	psi	8000
Tensile Modulus	ASTM D638	psi	410000
Elongation at Break	ASTM D638	%	20
Flexural Strength	ASTM D790	psi	12500
Flexural Modulus	ASTM D790	psi	450000
Compressive Strength	ASTM D695	psi	15000
Rockwell Hardness	ASTM D785		85
Rockwell Hardness	ASTM D785	R	115
Izod Impact, Notched	ASTM D256	ft-lb/in	0.7
Thermal properties			
Thermal Conductivity		in/hr/ft ² /°F	2.0
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	5.1
Melting Point		°F	347
Continuous Service Temperature, Air		°F	185

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/12/2025 • Release: 26/12/2024 • Version: 1.0
PIM-Version: 32 • PIM-ID: 717935 • PIM-Code: 32-16-153.126.223-11.5.8-2
Company-IDs: 23070

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	248
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	334
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	3.7
Dielectric strength	ASTM D149	V/mil	450
Surface resistivity	ASTM D257	Ω/cm	10 ¹⁶
Compliance properties			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/12/2025 • Release: 26/12/2024 • Version: 1.0
 PIM-Version: 32 • PIM-ID: 717935 • PIM-Code: 32-16-153.126.223-11.5.8-2
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

