

Technical Data Sheet

Trovidur[®] ES FB

Typical characteristics

- Easy processing, particularly by sewing or tacking, but also by welding, thermoforming and glueing
- Flame retardant, self-extinguishing after removal of flame
- High breaking and bending strength
- RoHS-compliant
- ELV-compliant
- WEEE-compliant
- RLAP-compliant
- Good impact strength

Typical industries

- Construction de machines et d'installations
- Technique d'emboutissage
- Bus et autocars

	Test method	Unit	Guideline value
General properties			
Densité	DIN EN ISO 1183-1	g / cm ³	1,41
Water absorption	DIN EN ISO 62	%	0,20
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	48
Elongation at break	DIN EN ISO 527	%	20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2500
Notched impact strength	DIN EN ISO 179	kJ / m ²	8
Shore hardness	DIN EN ISO 868	scale D	77
Ball indentation hardness	DIN EN ISO 2039-1	MPa	100
Thermal properties			
Thermal conductivity	DIN EN ISO 8302	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	75
Service Temperature		°C	-20 ... +60

	Test method	Unit	Guideline value
Heat deflection temperature	DIN EN ISO 75	°C	70
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Electrical properties			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	>10 ¹⁵
Surface resistivity	DIN EN 62631-3-2	Ohm	>10 ¹³

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. Information on the REACh regulation can be found in our Product Handling Information Sheets, in our REACh information letter as well as in the SCIP database.

