

### Technical Data Sheet

## Trovidur<sup>®</sup> ESV-EX

#### Product characteristics

- Highly impact resistant
- High UV and weather resistance
- Very good stretching behaviour for thermoforming
- RoHS-compliant
- ELV-compliant
- WEEE-compliant
- RLAP-compliant
- High cold impact strength
- Very good surface quality
- Flame retardant, self-extinguishing after removal of flame
- Good vacuum forming properties

#### Product industries

- Building industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,41
Water absorption	DIN EN ISO 62	%	0,20
Flammability (Thickness 1,5 mm)	BS 476 Part 7 (GB)		Class 1
VOC	ISO 16.000	conform	A+
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	45
Elongation at break	DIN EN ISO 527	%	20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2500
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	8
Shore hardness	DIN EN ISO 868	scale D	80
Ball Hardness	ISO 2039	MPa	100
Compressive strength	DIN EN ISO 604	MPa	65

#### Röchling Industrial SE & Co. KG - Troisdorf

Mülheimer Str. 26 - Geb. 115 • 53840 Troisdorf/DE • Tel. +49 2241 4820-0  
 info@roechling-plastics.com • www.roechling.com/industrial/troisdorf

Print: 05/05/2024 • Release: 20/09/2023 • Version: 2.0

PIM-Version: 396 • PIM-ID: 591095 • PIM-Code: 396-7-13.12.9.10.9.10.10.13.11.10-8-2



	Test method	Unit	Guideline value
Bending strength	DIN EN ISO 178	MPa	60
<b>Thermal properties</b>			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	76
Service Temperature		°C	-20 ... +60
Heat deflection temperature	DIN EN ISO 75	°C	70
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	>10 <sup>15</sup>
Surface resistivity	DIN EN 62631-3-2	Ohm	>10 <sup>13</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. Information on the REACh regulation can be found in our Product Handling Information Sheets, in our REACh information letter as well as in the SCIP database.