

Technical Data Sheet

Trovidur® NL red

PVC-U

Typical characteristics

- Identification colour red
- Uniform physical properties
- Good resistance to acids, lyes and salt solutions
- Flame retardant
- Self-Extinguishing after removal of the flame
- Good weldability
- Good thermoformability
- Good glueability
- Good impact strength

Typical industries

- Chemical Processing Industry
- Chemical storage tanks

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,40
Water absorption	DIN EN ISO 62	%	0,20
Flammability (Thickness 1 ... 3 mm)	DIN 4102		B1
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	62
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength	DIN EN ISO 179	kJ / m ²	2
Shore hardness	DIN EN ISO 868	scale D	85
Ball Hardness	ISO 2039	MPa	125
Compressive strength	DIN EN ISO 604	MPa	70
Bending strength	DIN EN ISO 178	MPa	80
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	76
Service Temperature		°C	-10 ... +60

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 05/12/2025 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 961 • PIM-ID: 591022 • PIM-Code: 961-18-11.27.20.14.11.16.34.3.162-7.7-5
 Company-IDs: 20000-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Heat deflection temperature	DIN EN ISO 75	°C	69
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Electrical properties			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁵
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹³
Dielectric strength	IEC 60243	kV / mm	12
Comparative tracking index	IEC 60112	CTI	600

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.