

Technical Data Sheet

Trovidur[®] PN grey

Product characteristics

- Uniform physical properties
- Flame retardant, self-extinguishing after removal of flame
- High resistance to acids, lyes and salt solutions
- Very good electrical insulation properties
- Easy processing by welding, thermoforming and glueing
- Good impact strength

Product industries

- Chemical Processing Industry
- Chemical storage tanks
- Mechanical Engineering Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,44
Water absorption	DIN EN ISO 62	%	0,20
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	56
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength	DIN EN ISO 179	kJ / m ²	4
Shore hardness	DIN EN ISO 868	scale D	82
Ball Hardness	ISO 2039	MPa	120
Compressive strength	DIN EN ISO 604	MPa	70
Bending strength	DIN EN ISO 178	MPa	80
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	75
Service Temperature		°C	-10 ... +60
Heat deflection temperature	DIN EN ISO 75	°C	67

Röchling Industrial SE & Co. KG - Troisdorf

Mülheimer Str. 26 - Geb. 115 • 53840 Troisdorf/DE • Tel. +49 2241 4820-0
info@roechling-plastics.com • www.roechling.com/industrial/troisdorf

Print: 01/05/2024 • Release: 20/09/2023 • Version: 1.0

PIM-Version: 393 • PIM-ID: 591001 • PIM-Code: 393-23-25.11.10.10.9.161-7.6.5-2



	Test method	Unit	Guideline value
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Electrical properties			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ohm * cm	>10 ¹⁵
Surface resistivity	DIN EN 62631-3-2	Ohm	>10 ¹³

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. Information on the REACH regulation can be found in our Product Handling Information Sheets, in our REACH information letter as well as in the SCIP database.

