

Technical Data Sheet

Polystone® PPs EL black extruded

PP-H

Typical characteristics

- Flame retardant
- Antistatic
- Electrically conductive

Typical industries

- Chemical Processing Industry
- Electronics
- Exhaust-air cleaning plants
- Ventilation plants

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>1,25
Flammability (Thickness 3 mm / 6 mm)	UL 94		V0
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1300
Notched impact strength	DIN EN ISO 179	kJ / m ²	>4
Shore hardness	DIN EN ISO 868	scale D	>65
Thermal properties			
Melting temperature	ISO 11357-3	°C	>145
Thermal conductivity	DIN 52612-1	W / (m * K)	0,22
Thermal capacity	DIN 52612	kJ / (kg * K)	1,70
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	120 ... 190
Service temperature, long term	Average	°C	0 ... 100
Service temperature, short term (max.)	Average	°C	130
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	81
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	10 ⁵
Surface resistivity	DIN EN 62631-3-2	Ω	10 ⁵

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Formulation is optimised for use in low-stress (square) pipeline construction.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 20/04/2026 • Release: 05/01/2026 • Version: 5.0
 PIM-Version: 1124 • PIM-ID: 590984 • PIM-Code: 1124-41-16.16.13-9.8.4.4-5.8
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)





ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 20/04/2026 • Release: 05/01/2026 • Version: 5.0
PIM-Version: 1124 • PIM-ID: 590984 • PIM-Code: 1124-41-16.16.13-9.8.4.4-5.8
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

