

Technický datový list

Durolight[®] S2

Vlastnosti produktu

- Low thermal conductivity
- High mechanical strength
- Glass-reinforced thermoset SMC high-pressure laminate developed for applications at cryogenic temperatures

Typické oblasti použití

- LNG pohony – Nízkoteplotní izolace
- Potrubí
- Subsea
- Zdravotní péče

	Testovací metoda	Jednotka	Orientační hodnota
Mechanické vlastnosti			
Hustota	ISO 1183	g / cm ³	1,95
Pevnost v ohybu ¹⁾ ⊥ 0°C	ISO 178	MPa	350
Pevnost v ohybu ¹⁾ ⊥ +50°C	ISO 178	MPa	300
Pevnost v ohybu ¹⁾ ⊥ +100°C	ISO 178	MPa	200
Pevnost v ohybu ¹⁾ ⊥ +150°C	ISO 178	MPa	110
Pevnost v ohybu ¹⁾ ⊥ -50°C	ISO 178	MPa	450
Pevnost v ohybu ¹⁾ ⊥ -150°C	ISO 178	MPa	600 ²⁾
Pevnost v ohybu ¹⁾ ⊥ -196°C	ISO 178	MPa	700 ²⁾
Pevnost v ohybu ¹⁾ ⊥ -100°C	ISO 178	MPa	510
Modul pružnosti v ohybu ¹⁾ ⊥ 0°C	ISO 178	MPa	18000
Pevnost v tlaku ⊥ 0 °C	ISO 604	MPa	450
Pevnost v tlaku ⊥ +50 °C	ISO 604	MPa	400
Pevnost v tlaku ⊥ +100 °C	ISO 604	MPa	250
Pevnost v tlaku ⊥ +150 °C	ISO 604	MPa	180
Pevnost v tlaku ⊥ -50 °C	ISO 604	MPa	550
70 / 5 000 Pevnost v tlaku ⊥ -100 °C	ISO 604	MPa	650
Pevnost v tlaku ⊥ -150 °C	ISO 604	MPa	750 ²⁾
Pevnost v tlaku ⊥ -196 °C	ISO 604	MPa	850 ²⁾
Pevnost v tahu II RT	ISO 527	MPa	180

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/DE • Tel. +49 5934 701-0

info@roechling-plastics.com • www.roechling.com/industrial/haren

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 12/04/2026 • Vydáno: 20/09/2023 • Verze: 1.0

PIM-verze: 1066 • PIM-ID: 716643 • PIM-kód: 1066-44-12.23.9-3.5.5.27-20

Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Testovací metoda	Jednotka	Orientační hodnota
Rázová houževnatost \perp (Charpy) RT	ISO 179	kJ / m ²	200
Smyková pevnost II RT	DIN EN 60893	MPa	25
Tepelné vlastnosti			
Tepelná vodivost \perp RT		W / (m * K)	≈ 0,38 ^{2) 3)}
Tepelná vodivost \perp - 50 °C		W / (m * K)	≈ 0,35 ^{2) 3)}
Tepelná vodivost \perp - 196 °C		W / (m * K)	≈ 0,27 ^{2) 3)}
Fyzikální vlastnosti			
Absorpce vody (metoda 1)	ISO 62	%	0,2

\perp = perpendicular to the lamination II = parallel to the lamination

¹⁾ Sample size 80 x 10 x 4 mm, support distance 64 mm, tension zone unmachined

²⁾ Extrapolated value

³⁾ Thermal conductivity calculated by means of reference measurements on samples of 300 x 200 x 10 mm

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: www.roechling-industrial.com/gtc

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/DE • Tel. +49 5934 701-0

info@roechling-plastics.com • www.roechling.com/industrial/haren

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 12/04/2026 • Vydáno: 20/09/2023 • Verze: 1.0

PIM-verze: 1066 • PIM-ID: 716643 • PIM-kód: 1066-44-12.23.9-3.5.5.27-20

Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

