



## Technický datový list

# Polystone<sup>®</sup> P HG EHS white stisknuto

PP-H

### Vlastnosti produktu

- Good sterilisation resistance
- High rigidity
- ISO 10993-5 tested on semi-finished product
- Corrosion resistant
- Chemical resistant

### Typické oblasti použití

- Zdravotní péče

	Testovací metoda	Jednotka	Orientační hodnota
<b>Obecné vlastnosti</b>			
Hustota	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,91
Absorpce vody	DIN EN ISO 62	%	0,10
Hořlavost (tloušťka 3 mm / 6 mm)	UL 94		HB
<b>Mechanické vlastnosti</b>			
Mez kluzu	DIN EN ISO 527	MPa	>30
Modul pružnosti v tahu	DIN EN ISO 527	MPa	>1800
Vrubová houževnatost	DIN EN ISO 179	kJ / m <sup>2</sup>	>6
Tvrdość Shore	DIN EN ISO 868	scale D	>70
<b>Tepelné vlastnosti</b>			
Teplota tání	ISO 11357-3	°C	162 ... 167
Tepelná vodivost	DIN 52612-1	W / (m * K)	0,20
Tepelná kapacita	DIN 52612	kJ / (kg * K)	1,70
Koeficient lineární teplotní roztažnosti	DIN 53752	10 <sup>-6</sup> / K	120 ... 190
Teplota tepelné deformace	DIN EN ISO 75, Verf. A, HDT	°C	90
Teplotní odolnost při autoklávování	Průměr	°C	0 ... 135
<b>Elektrické vlastnosti</b>			
Objemový odpor	DIN EN 62631-3-1	Ω * cm	>10 <sup>14</sup>
Povrchový odpor	DIN EN 62631-3-2	Ω	>10 <sup>14</sup>
Dielektrická pevnost	IEC 60243	kV / mm	>40

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/04/2026 • Vydáno: 03/02/2025 • Verze: 5.0  
 PIM-verze: 844 • PIM-ID: 751508 • PIM-kód: 844-26-21.11.19.21.33-27-7.5  
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



This material is not intended for the use in medical products that remain for more than 24 hours in the human body or are intended to remain in contact with internal human tissue or blood for more than 24 hours. The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/04/2026 • Vydáno: 03/02/2025 • Verze: 5.0  
PIM-verze: 844 • PIM-ID: 751508 • PIM-kód: 844-26-21.11.19.21.33-27-7.5  
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

