

Technisches Datenblatt

Fibracon[®] PTFE Detectaflon

Typische Eigenschaften

- X-ray and metal detectable
- Easy to clean, withstands chemical cleaning products and other cleaning processes

Typische Industrien

- Chemischer Behälter- und Anlagenbau
- Fahrzeugbau
- Elektronik
- Öl und Gas
- Maschinen- und Anlagenbau
- Healthcare
- Lebensmittelindustrie
- Windkraft

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
Specific Gravity	ASTM D4894	-	2.32
Mechanische Eigenschaften			
Hardness	Needle	Shore D	63
Zugfestigkeit (23°C)	ASTM D4894	MPa	28
Reißdehnung	ASTM D4894	%	300
Coefficient of friction (Dynamic)	ISO 7148 *	-	0.22
Wear rate	ISO 7148 *	mm/h	0.022
Thermische Eigenschaften			
Gebrauchstemperaturbereich		°C	-200 to +260

This data provides typical values on a small selection of properties of the material, and should only be used as a guide to the generic material performance.

*ISO 7148 - Tribo starting conditions Pin on ring ISO 7148 Load= 3.5 N Rotating Speed= 4 m/sec Temp.= 80°C Counter-surface= STST Ra= 0.25-0.35 μm Contact area of the pin: 78.5 mm²

