

Technical Data Sheet

Trovidur® EC Clad LS

PVC-U

Typical characteristics

- Protección contra incendios según EN 13501 B - s2, d0
- Buena resistencia al impacto
- buena soldabilidad
- Good glueability
- Resistencia química
- Procesamiento fácil

Typical industries

- Sector de la construcción
- Tecnología de salas blancas
- Healthcare
- Industria alimentaria
- Construcción de contenedores químico

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,44
Water absorption	DIN EN ISO 62	%	1,0
Flammability	UL 94		V0
Flammability	ASTM E 84		Class 1/A - 2,5 mm
Flammability	EN 13501		B - s2, d0
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	50
Elongation at break	DIN EN ISO 527	%	20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2700
Notched impact strength	DIN EN ISO 179	kJ / m ²	4
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,18
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	60-80
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	75
Flammability properties			
Electrical properties			
Dielectric constant	IEC 60250		3,20
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{13}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2026 • Release: 10/10/2024 • Version: 4.0
PIM-ID: 709779 • PIM-Code: 84-21-11.162.16.3.33.12-10.7.27.5.9-5
Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

