

### Technical Data Sheet

# Trovidur<sup>®</sup> PN grey

PVC-U

#### Typical characteristics

- Propiedades físicas uniformes
- Retardante de llama
- Autoextinguible tras retirar la llama.
- Alta resistencia a ácidos, lejías y soluciones salinas.
- Aislamiento eléctrico
- Buena soldabilidad
- Buena termoformabilidad
- Good glueability
- Buena resistencia al impacto

#### Typical industries

- Construcción de contenedores químico
- Tanques de almacenamiento
- Construcción de máquinas e instalaciones

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,44
Water absorption	DIN EN ISO 62	%	0,20
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	56
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	4
Shore hardness	DIN EN ISO 868	scale D	82
Ball Hardness	ISO 2039	MPa	120
Compressive strength	DIN EN ISO 604	MPa	70
Bending strength	DIN EN ISO 178	MPa	80
<b>Thermal properties</b>			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	75
Service Temperature		°C	-10 ... +60
Heat deflection temperature	DIN EN ISO 75	°C	67

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>15</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	>10 <sup>13</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. Information on the REACH regulation can be found in our Product Handling Information Sheets, in our REACH information letter as well as in the SCIP database.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 02/05/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 591001 • PIM-Code: 1090-24-27.16.11.20.13.16.34.3.162-9.7.5-2  
 Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

