

テクニカルデータシート

Polystone[®] M PIR blue

PE-UHMW / PE 1000

製品の特徴

- 良好な耐摩耗性
- Good cutting resistance
- 優れた耐傷性
- 良好な衝撃強度

製品の用途例

- 機械工学

Sustainability

- Post-Industrial-Recycling material
- Recycling content 90%

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	>0,93
吸水率	DIN EN ISO 62	%	<0,01
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	>17
降伏伸び	DIN EN ISO 527	%	>18
引張破壊呼び歪	DIN EN ISO 527	%	>235
引張弾性率	DIN EN ISO 527	MPa	>550
ノッチ付き衝撃耐性	DIN EN ISO 11542	kJ / m ²	>100
ショア硬度	DIN EN ISO 868	scale D	>60
熱的物性			
融点	ISO 11357-3	°C	130 ... 135
熱伝導率	DIN 52612-1	W / (m * K)	0,40
線膨張係数	DIN 53752	10 ⁻⁶ / K	150 ... 230
使用温度 (長期)	平均値	°C	-250 ... 80
使用温度 (短期、最大)	平均値	°C	130
電気的物性			
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
表面固有抵抗	DIN EN 62631-3-2	Ω	>10 ¹⁴

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 28/02/2026 • Release: 20/02/2026 • Version: 2.0
PIM-Version: 49 • PIM-ID: 775944 • PIM-Code: 49-29-143.9.23.162-5-4.10-5

Page 1 / 1 (Dates in DD/MM/YYYY)

