

テクニカルデータシート

Polystone® Safe-Tec L

PE-HD / PE 300

製品の特徴

- 耐候性
- 濡れた路面でも滑りにくい
- 優れた加工性
- 表面と切断面の溶接が可能
- 溶剤や可塑剤の排出がない
- 優れた吸音性
- 振動減衰性

製品の用途例

- 遊技場
- ポート
- 船およびポート
- スポーツ・レジャー

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	>0,95
吸水率	DIN EN ISO 62	%	<0,01
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
燃焼性 (厚み 3 - 10 mm)	DIN 4102		B2
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	>22
引張破壊呼び歪	DIN EN ISO 527	%	>50
引張弾性率	DIN EN ISO 527	MPa	>1000
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m ²	>10
シヨア硬度	DIN EN ISO 868	scale D	>60
熱的物性			
融点	ISO 11357-3	°C	130 ... 135
熱伝導率	DIN 52612-1	W / (m * K)	0,40
熱容量	DIN 52612	kJ / (kg * K)	1,90
線膨張係数	DIN 53752	10 ⁻⁶ / K	150 ... 230
使用温度 (長期)	平均値	°C	-50 ... 100
使用温度 (短期、最大)	平均値	°C	100
ビカットB軟化温度	DIN EN ISO 306, Vicat B	°C	67

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/12/2025 • Release: 11/11/2024 • Version: 1.0

PIM-Version: 1001 • PIM-ID: 591162 • PIM-Code: 1001-33-61.13.12.11.12.10.10-8.11.5.3-5.5

Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
電氣的物性			
誘電率	IEC 60250		2,4
誘電正接 (10 ⁶ Hz)	IEC 60250		0,0004
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
表面固有抵抗	DIN EN 62631-3-2	Ω	>10 ¹⁴
比較トラッキング指数	IEC 60112		600
絶縁破壊電圧	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

One-sided coating can lead to unpreventable material distortion under certain circumstances.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/12/2025 • Release: 11/11/2024 • Version: 1.0
PIM-Version: 1001 • PIM-ID: 591162 • PIM-Code: 1001-33-61.13.12.11.12.10.10-8.11.5.3-5.5
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

