

テクニカルデータシート

Robatube EPDM black

EPDM

製品の特徴

- 耐薬品性
- 優れたストローク特性
- 高温耐性

製品の用途例

- 製紙

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	1,14
吸水率	DIN EN ISO 62	%	0,74
色			black
保管期間			~ 3
機械的物性			
シヨア硬度	DIN EN ISO 868	scale A	60
引張強度	internal method	MPa	9,5
最大圧力	internal method	bar	1,5
バースト圧力	internal method	bar	> 1,5
引張破壊呼び歪	internal method	%	> 400
熱的物性			
使用温度 (長期)	平均値	°C	-35 ... 120

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

The burst pressure was determined at a temperature of 20°C (ocular).

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 12/12/2025 • Release: 20/09/2023 • Version: 2.0
PIM-Version: 27 • PIM-ID: 709773 • PIM-Code: 27-3-33.10.11-8-2
Company-IDs: 21510

Page 1 / 1 (Dates in DD/MM/YYYY)

