Röchling

Save Energy in Conveying Systems by Using High-Performance LubX[®] Materials

• Sprockets

• Belt guides

• Guide rails

• Lane dividers

Rollers

Roechling Industrial North America offers two high-performance materials specially formulated for the material handling and conveying industry. With outstanding dry-running properties and lower coefficient of friction than standard UHMW-PE, **LubX® C** and **LubX® CV** reduce energy needs and all but eliminate slip-stick (backsliding).

LubX[®] C:

The original high-performing material

- Outstanding dry-running properties and up to 75% lower coefficient of friction than standard UHMW-PE means less energy is needed to run conveyor systems
- Designed for increased efficiency when sliding against POM and stainless steel/steel materials
- LubX[®] C reduces noise levels in factory environments, increasing overall safety for workers
- FDA compliant for use in food grade applications
- Reduced chances of slip-stick and backsliding
- Increase process efficiency and stability



LubX[®] C and LubX[®] CV application possibilities:

- Straight and curved chain tracks
- Gears
- Sorter push blocks
- Under-chain wear strips
- Wear strips

- LubX[®] CV: Designed for higher speeds and productivity
- LubX[®] CV has been developed with the same excellent sliding properties as LubX[®] C, but with the added benefit of lower temperature production for use in systems operating at higher speeds and pressure loads
- Excellent dry-running properties with a significantly lower coefficient of friction than UHMW-PE
- Uses less energy in high velocity conveyor systems
- High wear resistance and shorter run-in phase for longer maintenance intervals
- Easily machinable for use in complex parts
- LubX[®] CV reduces noise levels in factory environments, increasing overall safety for workers
- FDA compliant for use in food grade applications



$LubX^{\circledast}$ C and $LubX^{\circledcirc}$ CV are available in the following:

- Extruded profiles and rods
- Sheets in thicknesses up to 4"
- Standard colors:
 - ∘ LubX® C: Blue-grey
 - ∘ LubX® CV: Blue

Roechling Industrial. Empowering Industry. www.roechling.com/us/industrial



09/202



Industrial

LubX[®] – The Energy Savers

Tribological Systems

In the development of LubX[®] products, great care has been taken not only to minimize the coefficient of friction of the sliding materials, but also to consider the tribological system of the sliding partners in an integrated manner and especially aligned to the particular specific requirement concerned.

The individual motion and transport segments of different conveying systems were analyzed, and the relative movements of the elements and the friction forces arising at the points of contact examined. These frictional forces have a decisive impact on the performance of the conveying system.

Energy Efficiency

When utilizing components with optimized sliding properties in conveying processes, the conveying power required – and thus the energy applied – may be reduced to a minimum. The performance and efficiency of the plant can thus be considerably enhanced.



Coefficients of sliding friction under dry conditions | Validated on the application-related Roechling tribology test stand | Speed: 0.25 m/s / Surface pressure: 0.25 MPa / Test time: 24 h



Low Coefficient of Sliding Friction

Coefficient of sliding friction under dry conditions, validated on Roechling application-level tribology test apparatus, speed: 0.5 m/s, surface pressure 0.5 MPa, test time 24 hours

LubX[®] CV – For Higher Speed and Better Productivity



Traction on the drive during a complete chain run: Speed 0.68 m/s, Chemnitz University of Technology, Institute for Material Handling and Plastics

Low Temperature Development



Temperature development under dry conditions, validated on Roechling application-level tribology test apparatus, speed: 0.5 m/s, surface pressure 0.5 MPa, test time 24 hours



Pin-On-disc test conducted by the University of Erlangen/Institute of Polymer Engineering, steel disc: 100 Cr6, Rz 1.0 microns, surface pressure: p = 4.0 N/mn2, ambient temperature: Ta = 23° C, ambient medium: technically dry

©2021 Roechling Industrial Gastonia. All trademarks and service marks are property of Roechling Industrial Gastonia. All statements, technical information and recommendations contained in this publication are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Röchling Engineering Plastics cannot guarantee the accuracy or completeness of this information and it is the customer's responsibility.